

PCT


WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY-(PCT)

(51) International Patent Classification ⁶ : C08G 18/08, 18/28, 18/66		A1	(11) International Publication Number: WO 98/20058
			(43) International Publication Date: 14 May 1998 (14.05.98)
(21) International Application Number: PCT/EP97/05610 (22) International Filing Date: 10 October 1997 (10.10.97) (30) Priority Data: 96117643.5 4 November 1996 (04.11.96) EP (34) Countries for which the regional or international application was filed: DE et al. (71) Applicant: IMPERIAL CHEMICAL INDUSTRIES PLC [GB/GB]; Imperial Chemical House, Millbank, London SW1P 3JF (GB). (72) Inventors: SIEKER, Thomas, Heinrich; Josef-Schreiner-Strasse 16C, D-94469 Deggendorf (DE). GABRIELI, Franco; Via Piave 9, I-21020 Brebbia (IT). WALRAEDT, Saskia, Rachel; Hofakkerstraat 14, B-9052 Zwijnaarde (BE). (74) Agents: SWINNEN, Anne, Marie et al.; ICI Europe Ltd., ICI Polyurethanes, Intellectual Property Dept., Everslaan 45, B-3078 Everberg (BE).		(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, GH, HU, ID, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, UZ, VN, YU, ZW, ARIPO patent (GH, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG). Published With international search report.	

(54) Title: RIGID POLYURETHANE FOAMS



(57) Abstract

Polyol blend comprising a polyester polyol, a tertiary amine catalyst and an organic carboxylic acid wherein said carboxylic acid contains at least one OH, SH, NH₂ or NHR functional group, wherein R is an alkyl, cycloalkyl or aryl group and the use of said polyol blend in the manufacture of rigid polyurethane foams.

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

DESCRIPTION

RIGID POLYURETHANE FOAMS

5 This invention relates to rigid polyurethane or urethane-modified polyisocyanurate foams, to processes for their preparation and to polyol blends for use in said processes.

10 Rigid polyurethane and urethane-modified polyisocyanurate foams are in general prepared by reacting a stoichiometric excess of polyisocyanate with isocyanate-reactive compounds in the presence of blowing agents, surfactants and catalysts. One use of such foams is as a thermal insulation medium in, for example, buildings.

15 Polyether polyols or polyester polyols are generally used as isocyanate-reactive compounds.

Polyester polyols impart excellent flame retardancy characteristics to the resulting polyurethane foams and are in some cases even less expensive than polyether polyols.

20 There is a problem in respect of the stability of polyol blends containing polyester polyols and tertiary amine catalysts. It has been proposed to solve this problem by adding an organic carboxylic acid (such as formic acid, acetic acid, 2-ethylhexanoic acid) to the polyol blend (see US-P-
25 4,758,605). In order to retain the reactivity over prolonged storage catalyst levels need to be increased. Whereas the instability problem can be solved successfully in this way the processing of these systems is still uncontrollable which is reflected in the rise profile of the rising foam when the polyol blend is reacted with the polyisocyanate composition.

30 Therefore it is an object of the present invention to provide polyol blends containing polyester polyols and tertiary amine catalysts not showing the disadvantages mentioned above.

35 According to the present invention polyol blends are provided comprising a polyester polyol, a tertiary amine catalyst and an organic carboxylic acid wherein said carboxylic acid contains at least one OH, SH, NH₂ or NHR functional group, wherein R is an alkyl, cycloalkyl or aryl group.

40 The polyol blends of the present invention are stable for several weeks. Improved reaction profiles are obtained when these polyol blends are used to make rigid polyurethane foams; the cream time is decreased while at the same time the expansion of the foam at string time is almost complete.

Carboxylic acids to be used in the present invention have the general formula $X_n - R' - (COOH)_m$, wherein X is OH, SH, NH_2 or NHR, R' is an at least divalent hydrocarbon moiety, typically an at least divalent linear or branched aliphatic hydrocarbon moiety and/or an at least divalent alicyclic or aromatic hydrocarbon moiety, n is an integer having a value of at least 1 and allows for mono and polyfunctional substitution on the hydrocarbon moiety, m is an integer having a value of at least 1 and allows for mono and polycarboxyl substitution on the hydrocarbon moiety.

The "at least divalent hydrocarbon moiety" can be a saturated or unsaturated moiety of 1 to 20 carbon atoms, including a linear aliphatic moiety, a branched aliphatic moiety, an alicyclic moiety or an aromatic moiety. Stated otherwise, R' can, for example, be a linear or branched alkylene group of 1 to 10 carbon atoms, a cyclic alkylene group of 4 to 10 carbon atoms, or an arylene, an alkarylene or an ararylene group of 6 to 20 carbon atoms. Specific non-limiting examples of suitable hydrocarbon moieties are methylene, ethylene, n-propylene, isopropylene, n-butylene, isobutylene, n-amylene, n-decylene, 2-ethylhexylene, o-, m-, p-phenylene, ethyl-p-phenylene, 2,5-naphthylene, p,p'-biphenylene, cyclopentylene, cycloheptylene, xylylene, 1,4-dimethylenephenylene and the like. While above-noted radicals have two available substitution sites, at least one for a carboxyl group and one for a OH, SH, NH_2 or NHR group, it is contemplated that additional hydrogens on the hydrocarbon could be replaced with further carboxyl and/or OH, SH, NH_2 or NHR groups.

The carboxylic acids useful in the practice of the present invention generally have molecular weights below about 250.

The following carboxylic acids are illustrative of compounds suitable for practicing the present invention: citric acid, dimethylolpropionic acid, bis-(hydroxymethyl)propionic acid, bishydroxypropionic acid, salicylic acid, m-hydroxy benzoic acid, p-hydroxy benzoic acid, dihydroxybenzoic acid, glycolic acid, β -hydroxybutyric acid, cresotic acid, 3-hydroxy-2-naphthoic acid, lactic acid, tartaric acid, malic acid, resorcylic acid, hydroferulic acid, glycine, alanine, mercaptoacetic acid and the like.

Preferably X is OH, n is 1, R' is a linear or branched aliphatic hydrocarbon having 1 to 5 carbon atoms and m is 1, 2 or 3. Polycarboxylic acids are preferred. The hydroxyl group is preferably in α or β position with respect to the carboxyl group.

Most preferred carboxylic acids are lactic acid, glycolic acid, malic acid and citric acid.

At least one of said carboxylic acids is used; mixtures of two or more of these acids can be used as well.

Particularly preferred carboxylic acids for use in the present invention are malic acid or a combination of malic acid and citric acid, preferably in a weight ratio of between 75:25 and 25:75, most preferably in a weight ratio of about 1:1. Further improvements in reaction profile are observed.

5 The combination of malic acid and citric acid also leads to improvements in other physical properties of the obtained foam such as compression strength and adhesion; also less variation in density distribution.

10 The carboxylic acid is generally used in an amount ranging from 0.1 to 5 % by weight based on the isocyanate-reactive composition, preferably about 1 % to 3 %.

15 The term "polyester polyol" as used herein is meant to include any polyester polyol having a hydroxyl functionality of at least two wherein the majority of the recurring units contain ester linkages and the molecular weight is at least 400.

20 The polyester polyols for use in the present invention advantageously have an average functionality of about 1.8 to 8, preferably about 2 to 6 and more preferably about 2 to 2.5. Their hydroxyl number values generally fall within a range of about 15 to 750, preferably about 30 to 550, more preferably 70 to 550 and most preferably about 200 to 550 mg KOH/g. The molecular weight of the polyester polyol generally falls within the range of about 400 to about 10000, preferably about 1000 to about 6000.

25 Preferably the polyester polyols have an acid number between 0.1 and 20 mg KOH/g; in general the acid number can be as high as 90 mg KOH/g.

30 The polyester polyols of the present invention can be prepared by known procedures from a polycarboxylic acid or acid derivative, such as an anhydride or ester of the polycarboxylic acid, and any polyhydric alcohol. The polyacid and/or polyol components may be used as mixtures of two or more compounds in the preparation of the polyester polyols.

35 The polyols can be aliphatic, cycloaliphatic, aromatic and/or heterocyclic. Low molecular weight aliphatic polyhydric alcohols, such as aliphatic dihydric alcohols having no more than about 20 carbon atoms are highly satisfactory. The polyols optionally may include substituents which are inert in the reaction, for example, chlorine and bromine substituents, and/or may be unsaturated. Suitable amino alcohols, such as, for example,

40 monoethanolamine, diethanolamine, triethanolamine, or the like may also be used. A preferred polyol component is a glycol. The glycols may contain heteroatoms (e.g., thiodiglycol) or may be composed solely of carbon, hydrogen and oxygen. They are advantageously simple glycols of the general formula $C_nH_{2n}(OH)_2$ or polyglycols distinguished by intervening ether linkages

in the hydrocarbon chain, as represented by the general formula $C_nH_{2n}O_x(OH)_2$. Examples of suitable polyhydric alcohols include: ethylene glycol, propylene glycol -(1,2) and -(1,3), butylene glycol -(1,4) and -(2,3), hexanediol -(1,6), octanediol -(1,8), neopentyl glycol, 1,4-bishydroxymethyl cyclohexane, 2-methyl-1,3-propane diol, glycerin, trimethylolethane, hexanetriol -(1,2,6), butanetriol -(1,2,4), quinol, methyl glucoside, triethyleneglycol, tetraethylene glycol and higher polyethylene glycols, dipropylene glycol and higher polypropylene glycols, diethylene glycol, glycerol, pentaerythritol, trimethylolpropane, sorbitol, mannitol, dibutylene glycol and higher polybutylene glycols. Especially suitable polyols are alkylene glycols and oxyalkylene glycols, such as ethylene glycol, diethylene glycol, dipropylene glycol, triethylene glycol, tripropylene glycol, tetraethylene glycol, tetrapropylene glycol, trimethylene glycol, tetramethylene glycol and 1,4-cyclohexanedimethanol (1,4-bis-hydroxymethylcyclohexane).

The polycarboxylic acid component may be aliphatic, cycloaliphatic, aromatic and/or heterocyclic and may optionally be substituted, for example, by halogen atoms and/or may be unsaturated. Examples of suitable carboxylic acids and derivatives thereof for the preparation of the polyester polyols include: oxalic acid, malonic acid, adipic acid, glutaric acid, succinic acid, pimelic acid, suberic acid, azelaic acid, sebacic acid, phthalic acid, phthalic acid anhydride, terephthalic anhydride, isophthalic acid, terephthalic acid, trimellitic acid, tetrahydrophthalic acid anhydride, pyromellitic dianhydride, hexahydrophthalic acid anhydride, tetrachlorophthalic acid anhydride, endomethylene tetrahydrophthalic anhydride, glutaric acid anhydride, maleic acid, maleic acid anhydride, terephthalic acid dimethylester, terephthalic acid-bis glycol ester, fumaric acid, dibasic and tribasic unsaturated fatty acids optionally mixed with monobasic unsaturated fatty acids, such as oleic acids.

While the polyester polyols can be prepared from substantially pure reactant materials, more complex ingredients can be used, such as the side-stream, waste or scrap residues from the manufacture of phthalic acid, terephthalic acid, dimethyl terephthalate, polyethylene terephthalate, and the like. These compositions can be converted by reaction with polyols to polyester polyols through conventional transesterification or esterification procedures.

The production of the polyester polyols is accomplished by simply reacting the polycarboxylic acid or acid derivative with the polyol component in a known manner until the hydroxyl and acid values of the reaction mixture fall in the desired range. After transesterification or esterification the reaction product can optionally be reacted with an alkylene oxide.

The term "polyester polyol" as used herein includes any minor amounts of unreacted polyol remaining after the preparation of the polyester polyol and/or unesterified polyol (e.g., glycol) added after the preparation. The polyester polyol can advantageously include up to about 40 % by weight free glycol. Preferably the free glycol content is from 2 to 30, more preferably from 2 to 15 % by weight of the total polyester polyol component.

Aliphatic and/or aromatic polyester polyols can be used according to the present invention.

Mixtures of two or more different polyester polyols can be used.

According to the present invention the polyester polyols described above can constitute the totality of the reactive mixture reacted with the polyisocyanate; it is understood, however, that these polyols could also be used mixed with other isocyanate-reactive compounds conventionally used in the art; preferably at least 10 %, more preferably at least 20 % by weight of the total isocyanate-reactive compounds are polyester polyols as described above.

The isocyanate-reactive compounds which can be employed in combination with the polyester polyols in the preparation of the rigid polyurethane foams of the present invention include any of those known in the art for that purpose. Of particular importance for the preparation of rigid foams are polyols and polyol mixtures having average hydroxyl numbers of from 300 to 1000, especially from 300 to 700 mg KOH/g, and hydroxyl functionalities of from 2 to 8, especially from 3 to 8. Suitable polyols have been fully described in the prior art and include reaction products of alkylene oxides, for example ethylene oxide and/or propylene oxide, with initiators containing from 2 to 8 active hydrogen atoms per molecule. Suitable initiators include: polyols, for example glycerol, trimethylolpropane, triethanolamine, pentaerythritol, sorbitol and sucrose; polyamines, for example ethylene diamine, tolylene diamine, diaminodiphenylmethane and polymethylene polyphenylene polyamines; and aminoalcohols, for example ethanolamine and diethanolamine; and mixtures of such initiators. Further suitable polymeric polyols include hydroxyl terminated polythioethers, polyamides, polyesteramides, polycarbonates, polyacetals, polyolefins and polysiloxanes.

Any organic compound containing at least one nitrogen atom, preferably a tertiary nitrogen atom and which is capable of catalysing the hydroxyl/isocyanate reaction can be used in the blends of the present invention.

Typical classes of tertiary amine catalysts include the N-alkylmorpholines, N-alkylalkanolamines, N,N-dialkylcyclohexylamines and alkylamines where the

alkyl groups are methyl, ethyl, propyl, butyl and the like and isomeric forms thereof; and heterocyclic amines. Typical but not limiting thereof are triethylenediamine, tetramethylethylenediamine, bis(2-dimethylaminoethyl)ether, triethylamine, tripropylamine, tributylamine, triamylamine, pyridine, quinoline, dimethylpiperazine, piperazine, N,N-dimethylcyclohexylamine, N-ethylmorpholine, 2-methylpiperazine, N,N-dimethylethanolamine, tetramethylpropanediamine, methyltriethylenediamine, 2,4,6-tri(dimethylaminomethyl)phenol, N,N',N"-tris(dimethylaminopropyl)-sym-hexahydrotriazine, and the like, and mixtures thereof. Also amines containing isocyanate-reactive groups such as aminoalcohols can be used; examples hereof include 2-(2-dimethylaminoethoxy)ethanol, trimethylaminoethylethanolamine and dimethylethylethanolamine. Preferred tertiary amine catalysts include triazines, dimethylbenzylamine, bis(dimethylaminoethyl)ether and dimethylcyclohexylamine. Especially dimorpholino diethylether, N-methylimidazole and dimethylamino pyridine are preferred; they further improve the reaction profile.

The tertiary amine catalyst is generally present in proportions of from about 0.01 to about 10 pbw per 100 pbw of polyol. Preferably the amount of amine is from about 0.1 to about 5 pbw, most preferably from about 0.2 to about 3 pbw per 100 pbw of polyol.

The blend of the present invention can also contain any of the blowing agents known in the art for the preparation of rigid polyurethane or urethane-modified polyisocyanurate foams. Such blowing agents include water or other carbon dioxide-evolving compounds, or inert low boiling compounds having a boiling point of above -70°C at atmospheric pressure.

Where water is used as blowing agent, the amount may be selected in known manner to provide foams of the desired density, typical amounts being in the range from 0.05 to 5 % by weight based on the total reaction system.

Suitable inert blowing agents include those well known and described in the art, for example, hydrocarbons, dialkyl ethers, alkyl alkanoates, aliphatic and cycloaliphatic hydrofluorocarbons, hydrochlorofluorocarbons, chlorofluorocarbons, hydrochlorocarbons and fluorine-containing ethers.

Examples of preferred blowing agents include isobutane, n-pentane, isopentane, cyclopentane or mixtures thereof, 1,1-dichloro-2-fluoroethane (HCFC 141b), 1,1,1-trifluoro-2-fluoroethane (HFC 134a), chlorodifluoromethane (HCFC 22), 1,1-difluoro-3,3,3-trifluoropropane (HFC 245fa) and blends thereof.

Particular mention may be made of blowing agent mixtures as described in PCT Patent Publication No. 96/12758, incorporated herein by reference, for

manufacturing low density, dimensionally stable rigid foam. These blowing agent mixtures generally comprise at least 3 and preferably at least 4 components of which preferably at least one is a (cyclo)alkane (preferably of 5 or 6 carbon atoms) and/or acetone.

The blowing agents are employed in an amount sufficient to give the resultant foam the desired bulk density which is generally in the range 15 to 70 kg/m³, preferably 20 to 50 kg/m³, most preferably 25 to 40 kg/m³. Typical amounts of blowing agents are in the range 2 to 25 % by weight based on the total reaction system.

When a blowing agent has a boiling point at or below ambient it is maintained under pressure until mixed with the other components. Alternatively, it can be maintained at subambient temperatures until mixed with the other components.

Other optional additives for the polyol blends of the present invention include crosslinking agents, for examples low molecular weight polyols such as triethanolamine, processing aids, viscosity reducers, dispersing agents, plasticizers, mold release agents, antioxidants, fillers (e.g. carbon black), cell size regulators such as insoluble fluorinated compounds (as described, for example, in US 4981879, US 5034424, US 4972002, EP 0508649, EP 0498628, WO 95/18176), non-amine polyurethane catalysts (e.g. stannous salts of carboxylic acids), trimerisation catalysts (e.g. alkali metal carboxylic acid salts), surfactants such as polydimethylsiloxane-polyoxyalkylene block copolymers and non-reactive and reactive fire retardants, for example halogenated alkyl phosphates such as tris chloropropyl phosphate, triethylphosphate, diethylethylphosphonate and dimethylmethylphosphonate. The use of such additives is well known to those skilled in the art.

Suitable organic polyisocyanates to be reacted with the polyol blends of the present invention to form rigid polyurethane or urethane-modified polyisocyanurate foams include any of those known in the art for the preparation of rigid polyurethane or urethane-modified polyisocyanurate foams, and in particular the aromatic polyisocyanates such as diphenylmethane diisocyanate in the form of its 2,4'-, 2,2'- and 4,4'-isomers and mixtures thereof, the mixtures of diphenylmethane diisocyanates (MDI) and oligomers thereof known in the art as "crude" or polymeric MDI (polymethylene polyphenylene polyisocyanates) having an isocyanate functionality of greater than 2, toluene diisocyanate in the form of its 2,4- and 2,6-isomers and mixtures thereof, 1,5-naphthalene diisocyanate and 1,4-diisocyanatobenzene. Other organic polyisocyanates which may be mentioned include the aliphatic diisocyanates such as

isophorone diisocyanate, 1,6-diisocyanatohexane and 4,4'-diisocyanatodicyclohexylmethane. Further suitable polyisocyanates for use in the process of the present invention are those described in EP-A-0320134.

5 Modified polyisocyanates, such as carbodiimide or uretonimine modified polyisocyanates can also be employed.

Still other useful organic polyisocyanates are isocyanate-terminated prepolymers prepared by reacting excess organic polyisocyanate with a minor amount of an active hydrogen-containing compound.

10 Preferred polyisocyanates to be used in the present invention are the polymeric MDI's.

The quantities of the polyisocyanate composition and the polyfunctional isocyanate-reactive composition to be reacted can be readily determined by
15 the man skilled in the art. In general the NCO:OH ratio falls within the range 0.85 to 1.40, preferably about 0.95 to 1.20. Also higher NCO:OH ratios (for example, up to 3.0) fall within the present invention.

In operating the process for making rigid foams according to the invention,
20 the known one-shot, prepolymer or semi-prepolymer techniques may be used together with conventional mixing methods and the rigid foam may be produced in the form of slabstock, mouldings, cavity fillings, sprayed foam, frothed foam or laminates with other materials such as hardboard, plasterboard, plastics, paper or metal.

25 According to one embodiment of the present invention the polyol blend as described above is reacted with a polyisocyanate composition to make rigid polyurethane foams.

30 According to another embodiment of the present invention the ingredients (polyester polyol, amine catalyst and carboxylic acid) are not added as a blend but are added separately to the reaction mixture.

The foams of the present invention are advantageously used for producing laminates whereby the foam is provided on one or both sides with a facing
35 sheet. The laminates can be made in a continuous or discontinuous manner by depositing the foam-forming mixture on a facing sheet and preferably placing another facing sheet on the deposited mixture. Any facing sheet previously employed to produce building panels can be employed and can be of a rigid or flexible nature.

40 The various aspects of this invention are illustrated, but not limited by the following examples in which the following ingredients are used:
Polyol A: a sorbitol initiated polyether polyol of OH value 460 mg KOH/g.
Polyol B: an aliphatic polyester polyol of OH value 356 mg KOH/g and acid

value 0.5 mg KOH/g.

Polyol C: an aromatic amine initiated polyether polyol of OH value 495 mg KOH/g.

Polyol D: a brominated polyether polyol of OH value 310 mg KOH/g.

5 Polyol E: an aromatic polyester polyol of OH value 240 mg KOH/g.

Polyol F: an aromatic polyester polyol of OH value 350 mg KOH/g.

Fire retardant A: a chlorinated flame retardant.

Fire retardant B: a phosphorous based flame retardant.

Surfactant: a silicone surfactant.

10 DMBA: dimethylbenzylamine catalyst available from Protex.

DMDEE: dimorpholinodiethylether catalyst available from Nitroil.

DMAP: dimethylaminopyridine catalyst available from Aldrich.

NMI: N-methyl imidazole catalyst available from BASF.

15 Polycat 41: tris(dimethylaminopropyl)hexahydrotriazine catalyst available from Air Products.

Niax A1: bis(dimethylaminoethyl)ether catalyst available from OSi.

Texacat DP914: a catalyst available from Texaco.

DMCHA: dimethylcyclohexylamine catalyst available from BASF.

SUPRASEC DNR: polymeric MDI available from Imperial Chemical Industries.

20 SUPRASEC is a trademark of Imperial Chemical Industries.

EXAMPLE 1

25 Rigid polyurethane foams were made from a polyol composition and a polyisocyanate composition containing the ingredients listed below in Table 1 at an NCO index of 1.15.

The reaction profile was followed in respect of cream time (time taken for the reaction mixture to start foaming) and string time (time taken for the reaction mixture to reach the transition point from fluid to cross-linked mass). The height of expansion was measured at the string time and also at the end of rise of the foam; from those two figures the expansion factor at string time (height at string/height at end of rise) was determined.

30 The results are also given in Table 1.

35 The rise profile was also followed by Dynamic Flow Data analysis. Results are presented in Figures 1, 2 and 3 expressing the height of the rising foam versus the reaction time.

These results show that whereas acetic acid leads to delayed action catalysis (Foam No. 2) addition of functionalised carboxylic acids of the present invention improves the reaction profile (Foam No. 3) (see Figure 1). Addition of selected classes of catalysts (for example, DMDEE, DMAP, NMI, Texacat DP914) (Foams No. 4, 5, 6, 7, 9) further improves the reaction profile (see Figure 2).

40 Glycolic acid (Foam No. 9) performs better than lactic acid (Foam No. 4) in terms of reaction profile improvement (see Figure 3).

Table 1

Foam No.	1	2	3	4	5	6	7	8	9
POLYOL									
Polyol A	pbw	20.5	20.5	20.5	20.5	20.5	20.5	20.5	20.5
Polyol B	pbw	23.0	23.0	23.0	23.0	23.0	23.0	23.0	23.0
Polyol C	pbw	10.0	10.0	10.0	10.0	10.0	10.0	10.0	10.0
Polyol D	pbw	21.0	21.0	21.0	21.0	21.0	21.0	21.0	21.0
acetic acid	pbw		1.0						
glycolic acid	pbw								1.0
lactic acid	pbw			1.1	1.1	1.1	1.1	1.1	
Fire retardant A	pbw	8.3	8.3	8.3	8.3	8.3	8.3	8.3	8.3
Fire retardant B	pbw	8.3	8.3	8.3	8.3	8.3	8.3	8.3	8.3
Surfactant	pbw	2.0	2.0	2.0	2.0	2.0	2.0	2.0	2.0
DMBA	pbw	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0
DMDEE	pbw			1.5					1.5
DMAp	pbw						0.3		
NMI	pbw				0.3				

[illegible]

EXAMPLE 2

The stability of the polyol blend of Foam No. 1 and Foam No. 3 (as identified above in Table 1) was determined by measuring cream time, string time and density of the foam prepared initially and after storage of the polyol blend for 3 days, 1 week and 3 weeks, respectively, at 40°C. The results are presented in Table 2 for Foam No. 1 and in Table 3 for Foam No. 3.

Table 2

Foam No. 1	Cream time (sec)	String time (sec)	Density (g/l)
Initial	17	154	27.6
After 3 days	18	185	28.0
After 1 week	20	245	29.0
After 3 weeks	24	267	29.6

Table 3

Foam No. 3	Cream time (sec)	String time (sec)	Density (g/l)
Initial	23	152	27.8
After 3 days	24	155	28.2
After 1 week	23	160	28.3
After 3 weeks	24	161	28.1

These results show that whereas there are relatively large variations in cream time, string time and density for Foam No. 1, these differences are only marginal for Foam No. 3. Thus stability of the polyol blends containing the functionalised carboxylic acids of the present invention is improved compared to polyol blends not containing said acids.

EXAMPLE 3

Rigid polyurethane foams were made from a polyol composition and a polyisocyanate composition containing the ingredients listed below in Table 4 at an NCO index of 1.15.

The reaction profile was followed in respect of cream time (time taken for the reaction mixture to start foaming) and string time (time taken for the

reaction mixture to reach the transition point from fluid to cross-linked mass). The height of expansion was measured at the string time and also at the end of rise of the foam; from those two figures the expansion factor at string time (height at string/height at end of rise) was determined.

5 The results are also given in Table 4.

It is to be noted that using citric acid or malic acid leads to the lowest density foam.

EXAMPLE 4

10

Rigid polyurethane foams were made from a polyol composition and a polyisocyanate composition containing the ingredients listed below in Table 5 at an NCO index of 1.15.

15

The reaction profile was followed in respect of cream time (time taken for the reaction mixture to start foaming) and string time (time taken for the reaction mixture to reach the transition point from fluid to cross-linked mass). The height of expansion was measured at the string time and also at the end of rise of the foam; from those two figures the expansion factor at string time (height at string/height at end of rise) was determined.

20

The results are also given in Table 5.

The rise profile was also followed by Dynamic Flow Data analysis. Results are presented in Figure 4 expressing the height of the rising foam versus the reaction time for Foams Nos 18, 19 and 20.

25

These results show that further improvements in reaction profile are obtained when malic acid (Foam No. 19) or a combination of malic acid and citric acid (Foam No. 20) are used instead of lactic acid (Foam No. 18).

Table 4

Foam No.		10	11	12	13	14	15	16	17
POLYOL									
Polyol A	pbw	20.5	20.5	20.5	20.5	20.5	20.5	20.5	20.5
Polyol B	pbw	23.0	23.0	23.0	23.0	23.0	23.0	23.0	23.0
Polyol C	pbw	10.0	10.0	10.0	10.0	10.0	10.0	10.0	10.0
Polyol D	pbw	21.0	21.0	21.0	21.0	21.0	21.0	21.0	21.0
Lactic acid	pbw	1.1							
Tartaric acid	pbw		1.1						
4-Hydroxybenzoic acid	pbw			1.1					
Citric acid	pbw				1.1				
Salicylic acid	pbw					1.1			
Malic acid	pbw						1.1		
Glycolic acid	pbw							1.1	
Bis(hydroxymethyl)propionic acid	pbw								1.1
Fire retardant A	pbw	8.3	8.3	8.3	8.3	8.3	8.3	8.3	8.3
Fire retardant B	pbw	8.3	8.3	8.3	8.3	8.3	8.3	8.3	8.3

5

10

15

Surfactant	pbw	2.0	2.0	2.0	2.0	2.0	2.0	2.0	2.0	2.0	2.0	2.0
DMBA	pbw	1.0	1.1	0.5	1.0	1.25	0.6	0.8	0.5			
DMDEE	pbw	1.5	1.5	1.5	1.5	1.5	1.5	1.5	1.5			
water	pbw	3.3	3.3	3.3	3.3	3.3	3.3	3.3	3.3			
HCFC 141b	pbw	4.2	4.2	4.2	4.2	4.2	4.2	4.2	4.2			
POLYISOCYANATE												
SUPRASEC DNR	pbw	139	139	139	139	139	139	139	139			
Density	kg/m ³	30.9	32.6	33.1	30.5	32.1	30.8	31.8	32.5			
Cream time	sec	20	16	19	20	23	17	34	21			
String time	sec	110	113	107	103	107	110	125	110			
Expansion factor at string time	%	92	88	92	92	92	92	84	89			

Table 5

Foam No.		18	19	20	21	22
POLYOL						
5	Polyol A	pbw	20.5	20.5	20.5	20.5
	Polyol B	pbw	23.0	23.0	23.0	23.0
	Polyol C	pbw	10.0	10.0	10.0	10.0
	Polyol D	pbw	21.0	21.0	21.0	21.0
	Lactic acid	pbw	1.1			
10	Malic acid	pbw		1.0	0.5	0.25
	Citric acid	pbw			0.5	0.25
	Fire retardant A	pbw	8.3	8.3	8.3	8.3
	Fire retardant B	pbw	8.3	8.3	8.3	8.3
	Surfactant	pbw	2.0	2.0	2.0	2.0
15	DMBA	pbw	1.0	0.6	0.7	0.66
	DMDEE	pbw	1.5	1.5	1.5	1.5
	water	pbw	3.3	3.3	3.3	3.3
	HCFC 141b	pbw	4.2	4.2	4.2	4.2
POLYISOCYANATE						
20	SUPRASEC DNR	pbw	139	139	139	139
	Cream time	sec	20	13	13	17
	String time	sec	108	108	104	102
25	Expansion factor at string time	%	91.4	90.1	92.4	92.2

EXAMPLE 5

The stability of the polyol blend of Foam No. 19 and Foam No. 20 (as identified above in Table 5) was determined by measuring cream time, string time and density of the foam prepared initially and after storage of the polyol blend for 1 day, 4 days, 1 week and 2, 3, 4 and 5 weeks, respectively, at 40°C.

The results are presented in Table 6 for Foam No. 19 and in Table 7 for Foam No. 20.

Table 6

Foam No. 19	Cream time (sec)	String time (sec)	Density (g/l)
Initial	12	107	30.4
After 1 day	15	111	30.3
After 4 days	15	115	31.3
After 1 week	15	113	31.6
After 2 weeks	15	112	31.6
After 3 weeks	15	117	31.7
After 4 weeks	14	115	31.1
After 5 weeks	15	118	30.8

Table 7

Foam No. 20	Cream time (sec)	String time (sec)	Density (g/l)
Initial	15	106	30.8
After 1 week	15	115	30.3
After 2 weeks	15	108	30.3
After 4 weeks	15	110	31.2
After 5 weeks	15	108	30.1

EXAMPLE 6

Rigid polyurethane foams were made from a polyol composition and a polyisocyanate composition containing the ingredients listed below in Table 8 at an NCO index of 1.

The reaction profile was followed in respect of cream time (time taken for the reaction mixture to start foaming) and string time (time taken for the reaction mixture to reach the transition point from fluid to cross-linked mass). Free rise density was also determined.

The results are also given in Table 8.

Table 8

Foam No.		23	24	25
POLYOL				
5	Polyol A	pbw	21.4	21.4
	Polyol B	pbw	34.0	
	Polyol C	pbw	11.7	11.7
	Polyol D	pbw	11.0	11.0
	Polyol E	pbw	34.0	
10	Polyol F	pbw		34.0
	Lactic acid	pbw	1.1	1.1
	Fire retardant B	pbw	13.5	13.5
	Surfactant	pbw	1.8	1.8
	DMBA	pbw	1.2	1.0
15	DMDEE	pbw	0.9	0.9
	water	pbw	3.4	3.4
	HFC 134a	pbw	4.0	4.0
POLYISOCYANATE				
	SUPRASEC DNR	pbw	140	140
20	Cream time	sec	7	6
	String time	sec	95	95
	Free rise density	kg/m ³	27.6	28.0

CLAIMS

1. Isocyanate-reactive composition comprising a polyester polyol, an amine catalyst and a carboxylic acid characterised in that said carboxylic acid contains at least one OH, SH, NH₂ or NHR functional group wherein R is an alkyl, cycloalkyl or aryl group.
2. Isocyanate-reactive composition according to claim 1 wherein said carboxylic acid corresponds to the formula X_n - R' - (COOH)_m wherein X is OH, SH, NH₂ or NHR, R' is an at least divalent hydrocarbon moiety, n is an integer having a value of at least 1 and m is an integer having a value of at least 1.
3. Isocyanate-reactive composition according to claim 2 wherein X is OH, R' is a linear or branched aliphatic hydrocarbon having 1 to 5 carbon atoms, n is 1 and m is 1, 2 or 3.
4. Isocyanate-reactive composition according to claim 3 wherein said carboxylic acid is selected from the group consisting of lactic acid, glycolic acid, malic acid, citric acid.
5. Isocyanate-reactive composition according to claim 4 wherein as carboxylic acid is used a mixture of citric acid and malic acid at a weight ratio of about 1:1.
6. Isocyanate-reactive composition according to any one of the preceding claims wherein said carboxylic acid is used in an amount ranging from 0.1 to 5 % by weight based on the isocyanate-reactive composition.
7. Isocyanate-reactive composition according to any one of the preceding claims wherein the polyester polyol has an average functionality of 1.8 to 8, a hydroxyl number of 15 to 750 mg KOH/g and a molecular weight of 400 to 10000.
8. Isocyanate-reactive composition according to any one of the preceding claim wherein the polyester polyol constitutes at least 10 % by weight of the total isocyanate-reactive compounds.
9. Isocyanate-reactive composition according to any one of the preceding claims wherein said amine catalyst is a tertiary amine selected from the group consisting of N-alkylmorpholine, N-alkylalkanolamine, N,N-dialkylcyclohexylamine, alkylamine, heterocyclic amine.

10. Isocyanate-reactive composition according to any one of the preceding claims wherein said amine catalyst is dimorpholino diethylether or N-methylimidazole or dimethylamino pyridine or a triazine.
- 5 11. Isocyanate-reactive composition according to any one of the preceding claims wherein said amine catalyst is used in amounts varying between 0.1 and 5 % by weight based on the isocyanate-reactive composition.
- 10 12. Isocyanate-reactive composition according to any one of the preceding claims further comprising a blowing agent.
- 15 13. Process for making rigid polyurethane or urethane-modified polyisocyanurate foams comprising the step of reacting an organic polyisocyanate composition with an isocyanate-reactive composition characterised in that the isocyanate-reactive composition is as defined in any one of the preceding claims.
- 20 14. Process for making rigid polyurethane or urethane-modified polyisocyanurate foams comprising the step of reacting an organic polyisocyanate composition with an isocyanate-reactive composition comprising a polyester polyol in the presence of an amine catalyst and a carboxylic acid characterised in that said carboxylic acid is as defined in any one of claims 1 to 6.
- 25 15. Rigid polyurethane or urethane-modified polyisocyanurate foams obtainable by the process as defined in claim 13 or 14.




FIGURE 1




FIGURE 2




FIGURE 3




FIGURE 4

INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 97/05610

A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 C08G18/08 C08G18/28 C08G18/66

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 C08G

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	FR 1 228 289 A (IMPERIAL CHEMICAL INDUSTRIES) 29 August 1960 see page 1, column 1, line 4 - page 2, column 1, line 12; claim 1 ---	1-4
X	DE 44 44 249 A (BASF) 20 June 1996 see page 2, line 56 - page 5, line 44; claims 1,2,4-6; examples ---	1
A	WO 88 01545 A (ASHLAND OIL) 10 March 1988 see page 10, line 10 - page 11, line 17; claim 1 --- -/--	1

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

30 January 1998

Date of mailing of the international search report

12/02/1998

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl.
Fax: (+31-70) 340-3016

Authorized officer

Bourgonje, A

INTERNATIONAL SEARCH REPORT

Int. l. Application No

PCT/EP 97/05610

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP 0 656 383 A (OSI SPECIALTIES) 7 June 1995 see page 4, line 29 - page 6, line 7; claims & US 5 489 618 A cited in the application ---	1
A	EP 0 283 866 A (DOW) 28 September 1988 see page 2, line 45 - page 5, line 34; claims & US 4 758 605 A cited in the application -----	1

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/EP 97/05610

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
FR 1228289 A	29-08-60	GB 879167 A NL 103386 C	
DE 4444249 A	20-06-96	NONE	
WO 8801545 A	10-03-88	US 4760101 A AU 7916487 A EP 0323962 A US 4852629 A	26-07-88 24-03-88 19-07-89 01-08-89
EP 656383 A	07-06-95	US 5489618 A AU 7904494 A BR 9404764 A CA 2136261 A JP 7233234 A	06-02-96 08-06-95 09-04-96 30-05-95 05-09-95
EP 283866 A	28-09-88	US 4758605 A DK 128188 A JP 63295618 A	19-07-88 13-09-88 02-12-88